

	L #	Hits	Search Text	DBs
1	L1	1350	(maleiniz\$4 maleic) near5 polybutadiene	USPA T; US-P GPUB
2	L2	181	1 and (carbowax peg polyoxyalkylene polyoxyethylene)	USPA T; US-P GPUB
3	L4	46	3 and (water adj solub\$5)	USPA T; US-P GPUB
4	L5	1	4 and (styrene adj butadiene adj vinylpyridine)	USPA T; US-P GPUB
5	L6	1	4 and (styrene adj butadiene adj vinyl adj pyridine)	USPA T; US-P GPUB
6	L7	45	4 and styrene	USPA T; US-P GPUB
7	L8	7	7 and ((vinyl adj pyridine) vinylpyridine)	USPA T; US-P GPUB
8	L9	87	3 and styrene	USPA T; US-P GPUB
9	L10	9	9 and ((vinyl adj pyridine) vinylpyridine)	USPA T; US-P GPUB
10	L11	2	10 not 8	USPA T; US-P GPUB
11	L12	65	3 and (cord fiber dip\$4 tire)	USPA T; US-P GPUB
12	L13	57	12 not 10	USPA T; US-P GPUB

	L #	Hits	Search Text	DBs
13	L14	2	1 same ((methoxypolyethylene adj glycol) carbowax (polyethylene adj glycol adj monomethyl) polyoxyalkylene)	USPA T; US-P GPUB
14	L15	434	(maleiniz\$4 maleic) near5 polybutadiene	EPO; JPO; DERW ENT; IBM TDB
15	L16	55	15 and adhesive	EPO; JPO; DERW ENT; IBM TDB
16	L17	0	16 and ((methoxypolyethylene adj glycol) polyoxyalkylene)	EPO; JPO; DERW ENT; IBM TDB
17	L19	0	18 and ((vinyl adj pyridine) vinylpyridine)	EPO; JPO; DERW ENT; IBM TDB
18	L18	11	16 and styrene	EPO; JPO; DERW ENT; IBM TDB
19	L3	90	2 and adhesive	USPA T; US-P GPUB